

MECHANICAL, THERMAL AND MORPHOLOGICAL STUDIES OF
EPOXIDIZED PALM OIL / UNSATURATED POLYESTER /
MONTMORILLONITE COMPOSITES

SITI NOOR HIDAYAH BINTI MUSTAPHA

A thesis submitted in fulfilment of the
Requirements for the award of the degree of
Doctor of Philosophy (Polymer Engineering)

Faculty of Chemical and Energy Engineering
Universiti Teknologi Malaysia

JANUARY 2016

DEDICATION

‘For my lovely Mom and Dad, my sisters and my brothers’

ACKNOWLEDGEMENTS

In the name of Allah, the most gracious and the most merciful. Alhamdulillah, whose grace and blessing have led me to complete this thesis. Peace be upon the Prophet Muhammad, may Allah bless him.

I would like to express my ultimate gratitude and respect to my parents, Puan Habshah Sharif and Mr. Mustapha Hashim and also my sisters and brothers. Thank you so much for all your unconditional love, support and sacrifices. Your encouragement and support gave me the strength to endure the difficult times during my period of study. Also thanks for all your prayers that have made me the success that I am today.

My special acknowledgement and appreciation to my supportive main supervisor, Assoc. Prof. Dr. Abdul Razak Rahmat for his endless guidance and assistance throughout my studies. Thank you very much for his willingness, time and comments in evaluating my research papers and my thesis prior to submission. May Allah reward him and his generation abundantly according to his riches in kindness, insha Allah. I would also thank my co-supervisor, Dr. Agus Arsad and Dr. Yeong Shoot Kian for their concern and assistance during my period of study.

My special and utmost thanks to technical staff of Polymer Engineering Department especially the technical staff of Synthesis Polymer Laboratory, En. Suhee, En. Izad, En Azri and Miss Zainab. This project would never been completed without their guidance and help. Last but not least, my gratitude and thanks to my dear friends in N14. Your presence has made my PhD journey memorable and enjoyable. Finally, thanks to every other individual who made this research work possible but have not been personally mentioned here. Thank you all very much.

ABSTRACT

Nanocomposite consisting of natural fibre reinforced thermoset/vegetable oil/montmorillonite (MMT) nanofiller resin is among the latest technologies in nanocomposites production. It has contributed to better environment and increase the sustainability of the composite materials. To tap the abundance of palm oil in Malaysia, this study was conducted to produce a novel composite of kenaf fibre reinforced unsaturated polyester (UPE)/epoxidized palm oil (EPO)/MMT by resin transfer moulding (RTM) followed by oven curing. Benzoyl peroxide was used as an initiator and the composition was kept constant at 1.5 phr. The compositions of UPE/EPO resin were varied at 90/10, 80/20, 70/30 wt % and the MMT nanoclay were varied at 1, 1.5 and 2 phr for each formulation. The effects of different loading ratios of EPO and MMT in UPE/EPO/MMT and the different RTM mould angles in kenaf fibre reinforced UPE/EPO/MMT composite were studied in particular mechanical, morphology, thermal, and water absorption properties of the resin and composite. Pre-characterisations of UPE/EPO resin were carried out using Fourier transform infrared spectroscopy and differential scanning calorimetry. The results revealed that the oxirane rings of EPO were successfully opened and the resin successfully crosslinked at applied curing temperature. The addition of EPO has caused a decrease in glass transition temperature, tensile, flexural properties and an increase in elongation at break and impact strength, which indicated an increase in mobility and toughness of UPE chain. UPE/EPO blends also exhibited higher thermal stability than neat UPE. The addition of MMT nanoclay enhanced the mechanical and thermal properties of the resin. The optimum balance properties were obtained for UPE at 10 wt % EPO and 1.5 phr MMT nanoclay loadings. The best formulation was then carried out at 0°, 30° and 45° RTM mould angle with kenaf fibre reinforcement. 30° RTM mould angle gave the highest mechanical and thermal properties of the resulted kenaf fibre reinforced UPE/EPO/MMT composite.

ABSTRAK

Nanokomposit yang terdiri daripada gentian semulajadi yang diperkukuhkan dalam resin termoset/minyak sayuran (VO)/pengisi nano montmorilonit (MMT) adalah antara teknologi terkini dalam penghasilan komposit. Ia telah menyumbang kepada persekitaran yang lebih baik dan meningkatkan kemampanan bahan-bahan komposit. Untuk memanfaatkan lambakan minyak sawit di Malaysia, kajian ini telah dijalankan bagi menghasilkan satu komposit baru gentian kenaf bertetulang poliester tak tepu (UPE)/minyak sawit terepoksi (EPO)/MMT oleh acuan pemindahan resin (RTM) dan diikuti oleh pengawetan ketuhar. Benzoil peroksida telah digunakan sebagai pemula dan komposisinya telah digunakan pada kadar tetap, 1.5 bahagian peratus resin (phr). Komposisi adunan UPE/EPO telah diubah pada 90/10, 80/20, 70/30 % berat dan tanah liat nano MMT telah diubah pada 1, 1.5 dan 2 phr bagi setiap formulasi. Kesan nisbah muatan EPO dan MMT yang berbeza dalam UPE/EPO/MMT dan sudut acuan RTM yang berbeza dalam gentian kenaf bertetulang UPE/EPO/MMT komposit telah dikaji secara khusus dalam sifat-sifat mekanikal, morfologi, penyerapan haba, dan air bagi resin dan komposit. Pra-pencirian UPE/EPO resin telah dijalankan dengan menggunakan spektroskopi inframerah transformasi Fourier dan kalorimeter pengimbasan pembezaan. Keputusan telah menunjukkan bahawa cincin oxiran EPO telah berjaya dibuka dan resin telah berjaya terpaut silang pada suhu pengawetan yang digunakan. Penambahan EPO menyebabkan penurunan suhu peralihan kaca, tegangan, sifat lenturan dan peningkatan dalam pemanjangan pada waktu rehat dan kekuatan impak, yang menunjukkan peningkatan dalam kekuatan dan mobiliti rantai UPE. Penambahan EPO juga menghasilkan kestabilan haba yang lebih tinggi daripada haba kemas UPE resin. Di samping itu, penambahan tanah liat nano MMT menunjukkan peningkatan dalam sifat-sifat mekanikal dan haba resin. Sifat optimum keseimbangan telah diperoleh bagi UPE pada 10 % berat EPO dan 1.5 phr muatan tanah liat nano MMT. Formulasi resin yang terbaik ini kemudiannya diproses pada sudut acuan RTM 0°, 30° dan 45° dengan tetulang gentian kenaf. Sudut acuan RTM 30° memberikan sifat-sifat mekanikal dan haba tertinggi di dalam gentian kenaf bertetulang UPE/EPO/MMT komposit.

TABLE OF CONTENTS

CHAPTER	TITLE	PAGE
	DECLARATION	ii
	DEDICATION	iii
	ACKNOWLEDGEMENTS	iv
	ABSTRACT	v
	ABSTRAK	vi
	TABLE OF CONTENTS	vii
	LIST OF TABLES	xii
	LIST OF FIGURES	xiv
	LIST OF ABBREVIATIONS	xix
	LIST OF SYMBOLS	xxi
	LIST OF APPENDICES	xxiii
1	INTRODUCTION	1
	1.1 Background of Study	1
	1.2 Problem Statement	5
	1.3 Objectives of Study	7
	1.4 Scope of Study	8
2	LITERATURE REVIEW	10
	2.1 Biocomposite	10
	2.2 Palm oil and Its Properties	14
	2.3 Epoxidized Palm Oil	18
	2.4 Vegetable Oils Biocomposite	22

2.4.1	Ring Opening of Epoxidized Vegetable Oil	26
2.4.2	Applications of Natural Fibre Biocomposite	27
2.5	Unsaturated Polyester Resin (UPE)	27
2.5.1	Properties of Unsaturated Polyester Resin	32
2.6	Benzoyl Peroxide	33
2.7	Nanoclay	35
2.7.1	Cloisite 30B	39
2.7.2	Addition of Clisite 30B Nanoclays in Biobased Polymer	41
2.8	Kenaf Fibre	43
2.8.1	Chemical Composition and Properties of Kenaf Fibre	45
2.8.2	Surface Treatment of Kenaf Fibre	48
2.8.3	Prospect of Kenaf Fibre in Malaysia	49
2.9	Kenaf Fibre Reinforced Unsaturated Polyester (UPE) Composite	50
2.10	Kenaf Fibre Reinforced Biobased Resin Composite	53
2.11	Resin Transfer Moulding (RTM)	54
2.11.1	Important Parameters in RTM	57
2.11.2	Natural Fibre Reinforced Thermoset Resin Using RTM	58
2.11.3	Effects of Mould Design and Mould Angle on Resin Flow Properties in RTM	60
3	METHODOLOGY	62
3.1	Experimental Design	62
3.2	Materials	64
3.2.1	Unsaturated Polyester Resin	64
3.2.2	Epoxidized Palm Oil	65
3.2.3	Montmorillonite Nanoclay	65
3.2.4	Benzoyl Peroxide	66
3.2.5	Kenaf Fibre Mat	66

3.2.6	Other Chemicals Used	66
3.3	Apparatus	67
3.4	Formulations and Preparation of Blend	67
3.4.1	Preparation of UPE/EPO Resin	67
3.4.2	Preparation of UPE/EPO/MMT Resin	68
3.5	Kenaf Fibre Treatment	70
3.6	Preparation of Kenaf Fibre Reinforced UPE/EPO/MMT Composite using Resin Transfer Moulding	70
3.7	Characterization of Blends	71
3.7.1	Fourier Transform Infrared Spectroscopy	71
3.7.2	Differential Scanning Calorimetry	72
3.8	Mechanical Test	72
3.8.1	Tensile Test	72
3.8.2	Impact Test	72
3.8.3	Flexural Test	73
3.9	Thermal Analysis	73
3.9.1	Thermogravimetric Analysis	73
3.10	Dynamic Mechanical Analysis	73
3.11	Moisture Absorption	74
3.12	Morphological Study	75
3.12.1	Scanning Electron Microscopy	75
3.12.2	Transmission Electron Microscopy	75
4	RESULTS AND DISCUSSION	76
4.1	Effects of Epoxidized Palm Oil (EPO) Loadings on Unsaturated Polyester (UPE) / Epoxidized Palm Oil (EPO) Resin	76
4.1.1	Fourier Transform Infrared Spectroscopy	76
4.1.2	Differential Scanning Calorimetry (DSC)	80
4.1.3	Tensile Properties	83
4.1.4	Flexural Properties	86
4.1.5	Impact Properties	88

4.1.6	Thermogravimetric Analysis (TGA)	89
4.1.7	Dynamic Mechanical Analysis (DMA)	92
4.1.7.1	Storage Modulus	92
4.1.7.2	Tangent delta	94
4.1.8	Water Absorption	97
4.1.9	Morphological Study	98
4.2	Effect of Montmorillonite (MMT) Nanoclay Loadings on Unsaturated Polyester (UPE) / Epoxidized Palm Oil (EPO) Resin	102
4.2.1	Tensile Properties	102
4.2.2	Flexural Properties	107
4.2.3	Impact Properties	110
4.2.4	Thermogravimetric Analysis (TGA)	111
4.2.5	Dynamic Mechanical Analysis (DMA)	115
4.2.5.1	Storage Modulus	115
4.2.5.2	Tangent delta	118
4.2.6	Water Absorption	121
4.2.7	Structural and Morphological Study	124
4.2.7.1	Scanning Electron Microscopy (SEM)	124
4.2.7.2	Transmission Electron Microscopy (TEM)	127
4.2.8	Balanced Mechanical Properties	132
4.3	Effect of Mould Angle on Treated Kenaf Fibre Reinforced Unsaturated Polyester (UPE) / Epoxidized Palm Oil (EPO) / Montmorillonite (MMT) Composites Using Resin Transfer Moulding (RTM)	134
4.3.1	Tensile Test	134
4.3.2	Flexural Properties	138
4.3.3	Impact Properties	140
4.3.4	Dynamic Mechanical Analysis (DMA)	141
4.3.4.1	Storage Modulus	141

	4.3.4.2	Tangent delta	144
	4.3.5	Morphological Study	146
5		CONCLUSION AND RECOMMENDATIONS	150
	5.1	Conclusion	150
	5.2	Recommendations for Future Works	151
		REFERENCE	152
		Appendix A - F	176 - 189

LIST OF TABLES

TABLE NO.	TITLE	PAGE
2.1	Chemical structure of common fatty acids	16
2.2	Fatty acid profiles of various plant oils (%)	17
2.3	Major Groups of Clay Minerals	36
2.4	Sheet Structure for the Layers of Clay Minerals	37
2.5	Physical appearance of organic modified, cloisite 30B montmorillonite nanoclay	41
2.6	Chemical composition, moisture content and microfibrillar angle of plant fibres	46
2.7	Properties of natural (plant) and synthetic fibre	47
3.1	Properties of unsaturated polyester resin (Reversol P 9539 NW, Synthomer)	64
3.2	Physical and chemical properties of epoxidized palm oil	65
3.3	Physical and chemical properties of Cloisite 30B MMT nanoclay	65
3.4	Physical and chemical properties of BP	66
3.5	General properties of the other chemicals used	67
3.6	Formulation of resin blends	69
3.7	Composite sample preparation at different mould angle	71
4.1	Values of heat generated during a differential scan DSC of different UPE/EPO blends resin	82
4.2	Weight loss analysis by TGA of UPE/EPO resin	92
4.3	The T _g , maximum tan δ , peak width at half height and crosslinking density results of UPE/EPO resin at different EPO loadings	96

4.4	Weigh loss analysis by TGA of UPE resin and UPE/EPO blend resin at different MMT nanoclay loadings	115
4.5	The T _g , maximum tan δ , peak width at half height and crosslinking density results of UPE resin and UPE/EPO resin at different MMT nanoclay loadings	121
4.6	Fibre volume fraction and fibre weight fraction of UPE/kenaf composites and UPE/EPO/MMT/kenaf composites	137
4.7	Glass transition temperature, maximum tan δ value and peak width at half height of unmodified composite (UC) and modified composites (MC) at different mould angles	146

LIST OF FIGURES

FIGURE NO.	TITTLE	PAGE
2.1	Classification of biodegradable polymers	11
2.2	Concept of “sustainable” bio-based product	12
2.3	Carbon dioxide sequestrations	13
2.4	Structure of a typical triglyceride molecule of palm oil	15
2.5	Fatty acids as starting materials for the synthesis of novel fatty compounds: (1) oleic acid, (2) linoleic acid, (3) linolenic acid, (4) petroselinic acid, (5) erucic acid, (6) calendic acid, (7) a-eleostearic acid, (8) vernolic acid, (9) ricinoleic acid	17
2.6	Mechanism of epoxidation	19
2.7	Possible side reactions of epoxides (where R1 and R2 is aliphatic chain)	19
2.8	Structure of a possible triglyceride in oil and its epoxidised product	20
2.9	Raw materials for polymers from palm oil	21
2.10	Oxirane ring opening of epoxidized vegetable oils	26
2.11	Condensation reaction between a dirotic acid and a polyhydric alcohol	28
2.12	Diols and triols used for an unsaturated polyester resin	29
2.13	Acids and anhydrides used in unsaturated polyester resin	29
2.14	Schematic diagram showing all possible reactions in the styrene-unsaturated polyester copolymerization	31
2.15	Structure of benzoyl peroxide	33
2.16	Schematic growth of free radicals	33

2.17	Formation of microgel particles	34
2.18	Formation of free radical from initiator	35
2.19	Mechanism of the reaction of initiator into polyester	35
2.20	Theoretical formula and structure of montmorillonite	37
2.21	Schematic of different types of composites formed from the interaction of layered silicates and polymers: (a) phase-separated microcomposites, (b) intercalated nanocomposites, (c) exfoliated nanocomposite	38
2.22	Chemical structure of organically modified Cloisite 30B	40
2.23	Structure of kenaf fibre	44
2.24	Structure of a biofibre	46
2.25	Chemical structure of cellulose	47
2.26	Processing steps in resin transfer moulding	55
3.1	Experimental design flowchart	63
3.2	Schematic of resin injection during in RTM process	71
4.1	FTIR spectrum of UPE, EPO and UPE/EPO resin	77
4.2	Possible chemical reactions mechanism of UPE/EPO blend resin: a) oxirane ring opening, b) free radical chain growth polymerization, and c) complete reaction mechanism of UPE/EPO blend resin	79
4.3	Dynamic DSC scans of uncured UPE and UPE with various amount of EPO	82
4.4	Tensile modulus of neat UPE and UPE/EPO blends resin	84
4.5	Tensile strength of neat UPE and UPE/EPO blends resin	85
4.6	Elongation at break of neat UPE and UPE/EPO blends resin	85
4.7	Flexural modulus of neat UPE and UPE/EPO blends resin	87
4.8	Flexural strength of neat UPE and UPE/EPO blends resin	87
4.9	Izod impact strength of neat UPE and UPE/EPO blends resin	89
4.10	TGA micrograph (a) and derivatives thermogram (b) of UPE, EPO and UPE/EPO resins of different compositions	91

4.11	Plot of storage modulus vs. temperature at different compositions of EPO in UPE resin	93
4.12	Change in storage modulus of neat UPE containing EPO at 35 °C	94
4.13	Plot of $\tan \delta$ vs. temperature at different compositions of EPO in UPE resin	96
4.14	Water absorption of UPE at different weight percent loadings of EPO	98
4.15	Low magnification SEM images showing the tensile failure surface of UPE and various blend resin: a) neat UPE b) UPE containing 10 wt % EPO resin c) UPE containing 20 wt % EPO resin d) UPE containing 30 wt % EPO resin	101
4.16	High magnification SEM images showing the tensile failure surface of UPE and various blend resin: a) UPE containing 20 wt % EPO resin b) UPE containing 30 wt % EPO resin	101
4.17	Tensile modulus of neat UPE and UPE/EPO/MMT blends	105
4.18	Tensile strength of neat UPE and UPE/EPO/MMT blends	106
4.19	Tensile strength of neat UPE and UPE/EPO/MMT blends	107
4.20	Tensile strength of neat UPE and UPE/EPO/MMT blends	108
4.21	Flexural strength of neat UPE and UPE/EPO/MMT blends	110
4.22	Izod impact strength of neat UPE and UPE/EPO/MMT blends	111
4.23	Weight loss analysis by TGA of UPE resin at different MMT nanoclay loadings: (a) TGA curve (b) derivative curve	113
4.24	Weight loss analysis by TGA of UPE/EPO resin at different MMT nanoclay loadings: (a) TGA curve (b) derivative curve	114
4.25	Storage modulus of UPE resin at different MMT loading	117

4.26	Storage modulus of UPE with 10 wt % EPO resin at different MMT loadings	117
4.27	Tangent delta of UPE resin at different MMT loading	120
4.28	Tangent delta of UPE with 10 wt % EPO bioresin at different MMT loadings	120
4.29	Water absorption of UPE resin at different amount of MMT loadings	123
4.30	Water absorption of UPE/10 wt % EPO resin at different amount of MMT loadings	123
4.31	SEM images of the tensile failure surface of UPE resin with various MMT content: Low magnification (x250 mag) - a) neat UPE b) UPE/1 phr MMT nanoclays. High magnification (x1000 mag) c) UPE/1 phr MMT nanoclays d) UPE/1.5 phr MMT nanoclays e) UPE/2 phr MMT nanoclays	126
4.32	SEM images of the tensile failure surface of UPE/10 wt % EPO resin with various MMT content at x250 mag : a) UPE/10 wt % EPO without MMT b) 1 phr MMT nanoclays c) 1.5 phr MMT nanoclays d) 2 phr MMT nanoclays	127
4.33	TEM images of UPE at different MMT loadings: (a) 1 phr, (b) 1.5 phr and (c) 2 phr (d) high magnification of an intercalated particle at 1.5 phr MMT (magnification: x200 nm) (e) high magnification of an intercalated particle at 2 phr MMT (magnification: x200 nm)	130
4.34	TEM images of UPE/EPO resin at different MMT loadings: Low magnification, x1 μ m: (a) 10 wt % EPO, (b) 30 wt % EPO. High magnification, x500nm: (c) 10 wt % EPO (d) 30 wt % EPO	132
4.35	Balanced mechanical properties of UPE/EPO/MMT resin	133
4.36	Tensile strength and tensile modulus of unmodified and modified composites at different mould angles	137

4.37	Elongation at break of unmodified and modified composites at different mould angles	138
4.38	Flexural strength and flexural modulus of unmodified and modified composites at different mould angles	139
4.39	Impact strength of unmodified and modified composites at different mould angles	141
4.40	Plot of storage modulus against temperature of (a) unmodified composite and (b) modified nanocomposites at different mould angles	143
4.41	Plot of tangent delta against temperature: (a) unmodified composite (UC) and (b) modified composites (MC) at different mould angles	145
4.42	SEM micrographs of tensile fracture surfaces at x50, x250 and x1000 magnification: a) 0° angle unmodified composite, b) 0° angle modified composite, c) 30° modified composite, d) 45° modified composite	149

LIST OF ABBREVIATIONS

UPE	-	Unsaturated polyester resin
EPO	-	Epoxidized palm oil
MMT	-	Montmorillonite nanoclay
BP	-	Benzoyl peroxide
UPE/EPO	-	Unsaturated polyester/epoxidized palm oil
UPE/MMT	-	Unsaturated polyester/montmorillonite
UPE/EPO/MMT	-	Unsaturated polyester/epoxidized palm oil/montmorillonite
FWHM	-	Full width half maximum
PMC	-	Polymer matrix composite
CMC	-	Ceramix matrix composite
MMC	-	Metal matrix composite
FRP	-	Fibre reinforced polymer
PHA	-	Polyhydroxyalkanoates
PHB	-	Polyhydroxybutyrate
PHVB	-	Poly(3-hydroxybutyrate-co-3-hydroxyvalerate)
PLA	-	Polylactic acid
PCL	-	Polycaprolactone
PEA	-	Polyesteramides
PBSA	-	Polybutylene succinate adipate
EML	-	Epoxidized methyl linseedate
EMS	-	Epoxidized methyl soyate
PGO	-	Pongamia glabra seed oil
ESO	-	Epoxidized soybean oil
EAS	-	Epoxidized allyl soyate
AESO	-	Acrylated epoxidized soybean oil
KF	-	Keratin feather fibre
RTM	-	Resin transfer moulding

VARTM	- Vacuum assisted resin transfer moulding
SRIM	- Structural resin injection moulding
LCM	- Liquid composite moulding
FTIR	- Fourier transform infrared
DSC	- Dynamic scanning calorimetry
TGA	- Thermogravimetric analysis
DMA	- Dynamic mechanical analysis
XRD	- X-ray diffraction
SEM	- Scanning electron microscopy
TEM	- Transmission electron microscopy
ASTM	- American standard testing material
HDT	- Heat distortion temperature
MEKP	- Methyl ethyl ketone peroxide
NaOH	- Sodium hydroxide
KBr	- Calcium bromide
IUPAC	- International Union of Pure and Applied Chemistry

LIST OF SYMBOLS

wt %	-	Weight percent
e.g.	-	For example
i.e.	-	That is
°C	-	Degree celsius
m	-	Meter
mm	-	Millimetre
mm/min	-	Millimetre per minute
h	-	Hour
cm	-	Centimetre
cm ³	-	Centimetre cube
nm	-	Nanometre
m ²	-	Metre square
m ² /g	-	Metre square per gram
%	-	Percent
°C/min	-	Degree celsius per minute
GPa	-	Giga pascal
KPa	-	Kilo pascal
MPa	-	Mega pascal
Pa.s	-	Pascal second
L	-	Liter
kg	-	Kilogram
M	-	Molar
mg	-	Milligram
in	-	inch
J	-	Joule
kV	-	Kilovolts
mA	-	Milliampere

J/g	-	Joule per gram
phr	-	Part per hundred resin
R	-	Gas constant [8.314 J/K.mol]
E	-	Activation energy
T	-	Absolute temperature
k	-	Permeability
P	-	Pressure
ρ	-	Density
T _g	-	Glass transition temperature

LIST OF APPENDIX

APPENDIX	TITTLE	PAGE
A	Mould design and angle set up for resin transfer moulding	176
B	Calculation of crosslinking density using DMA result	179
C	Full width half maximum calculation using Gaussian function	182
D	Calculation of fibre weight fraction and fibre volume fraction	184
E	Abstract of publication in international journals	186
F	Abstract of publication in scopus and proceeding publications through international conferences	189

CHAPTER 1

INTRODUCTION

1.1 Background of Study

Composites are one of the wide spread areas that have been applied present due to the high performance of composites compared to neat polymer. Both thermoset and thermoplastic composites have widened the applications and improved the performance of polymer industries. Many composite industries have generated significant economic activity in many countries. Main industries that have applied composites materials include automotive, construction, furniture, aircraft, boat, chemical, electrical and sports industries (Richard, 2005). The manufacturers, designers, and engineers recognized the ability of composite materials to produce high quality and cost-effective products that are high strength, light weight, corrosion resistant, flexible in design and durable. These advantages are reflected in the high demand for composite products.

In order to increase the environmental concern of composite product, natural fibres have been used rather than synthetic fibres. Replacing synthetic fibre (such as glass fibre, carbon fibre and aramide fibre) with natural fibre has both environmental and economic advantages (Williams and Wool, 2000). Among the common natural fibre is kenaf. Kenaf, known by its scientific name as *Hibiscus Cannabinus*, L. has been cultivated for use in ropes and animal consumption for the last 4,000 years. Kenaf fibre has been produced mostly for textiles, gunny sacks and, to a certain extent, paper. Recently, kenaf fibre is also being applied in composite field. Due

to the increase in application of kenaf fibre, the crop has begun to attract much attention and interest of many countries. China, Indonesia, Myanmar, Thailand and United States of America are the traditional growers of kenaf for the world market. Malaysian Government is also heavily promoting the development of kenaf as the next major industrial crop for the country in line with its policy of developing new sources of economic growth. Up to February 2011, the Government had spent RM50 million under the purview of the Ministry of Plantation Industries and Commodities to develop kenaf through research and development in upstream and downstream areas (Khan, 2011). In 2012 and 2013, the federal government disbursed a total of 33 and 48 million RM respectively under the New Plant Kenaf Program (MPIC) which was developed to manage and develop the kenaf plant in Malaysia (Annual Report, 2013).

In composite industries, natural fibres including kenaf fibre are used as an alternative to form green composite, replacing the synthetic fibre commonly used previously. Many researchers have reported on natural fibre reinforced petroleum-based thermoplastic (Kozlowski *et al.*, 2004; Tajvidi *et al.*, 2006) and thermoset (Mohamed Yusoff, 2009; Trujillo *et al.*, 2010; Jawaid *et al.*, 2012; Adriana *et al.*, 2013) polymer. Even though natural fibre contributed to a better environment, natural fibre reinforced polymer resin composites are not sufficiently eco-friendly because of the petroleum-based source and the non-biodegradable nature of the polymer matrix (Mohanty *et al.*, 2002a). This phenomenon indicates that the development of natural fibre reinforced renewable source based resin is important. Other than solving the environmental issues, the composite from natural fibre and renewable source based resin is also increased the sustainability of the composite materials (Zhu *et al.*, 2004). Thus, developing the bioresin from renewable sources is a clear future prospect.

Over the past decade, natural oils, as a feedstock for thermosetting resin has gained a lot of attention due to their availability and low cost (Pfister and Larock, 2010). However, it was found that the use of plant oil based resin in composites has been limited, due to their lower mechanical and thermo-physical properties compared to synthetic resin. A promising compromise between environmental friendliness and

performance of bio-based resin was obtained by replacing part of a petroleum based resin with natural plant oil (Dutta and Karak, 2005). The most reported starting materials for bio-based thermoset resin are soybean oil (Haq *et al.*, 2008; Nava and Brooks, 2010; Tan and Chow, 2011a), linseed oil (Haq *et al.*, 2011), rapeseed oil and nahar oil (Dutta *et al.*, 2004; Mahapatra and Karak, 2004; Dutta and Karak, 2005). In addition, corn, olive and canola oil are being used as the starting raw material for bio-based resin (Williams and Wool, 2000). As reported by previous studies, the additions of plant oil in petroleum based thermoset resin has improved the toughness, barrier and thermal properties of the resulting bioresin system (Dutta and Karak, 2005; Haq *et al.*, 2008, 2009b, 2011). However, according to Haq *et al.* (2009a, 2009b), increase in toughness performance generally against the stiffness performance of the material. Thus, some filler needs to be added in order to have proper balance on toughness-stiffness (Haq *et al.*, 2008, 2009b) and improve certain properties of the bioresin.

Layered silicate nanoclay has been discussed in past decades as reinforcement filler in polymer nanocomposites industries. Polymers reinforced with nanoclays have been shown to exhibit enhancements in mechanical, thermal and barrier properties at low concentration. As reported in previous study, the MMT addition in vegetable oil based bioresin has recovered the decrease in stiffness, thermal and barrier properties of the bioresin due to addition of plant oil and it leads to improved stiffness-toughness balance of the bioresin (Miyagawa *et al.*, 2006b). Thus, the addition of nanoclay has leads to improved the stiffness-toughness balance of the resin and produced a polymer nanocomposite with similar or enhanced properties compared to the neat polymer (Haq *et al.*, 2008, 2009a, 2009b, 2011). This condition holds a great promise for the resin to be used in wide composite applications.

Palm oil is the world's highest yielding oil crop, which is abundantly available in South East Asian countries, especially in Indonesia and Malaysia (Biron, 2004). Malaysia is the second largest producer of palm oil in the world after Indonesia. According to the report from United States Department of Agriculture (USDA) (2015), 86 % of world production of palm oil in 2014/15 was dominated by

Malaysia and Indonesia. Palm oil is mostly used in food as cooking oil, shortening and margarine, while in oleochemicals industry, functionalized palm oil are used in manufacturing soaps, cosmetics, detergents, lubricants, glues, and also as raw material for biodiesel. In the last few decades, palm oil applications in the pharmaceutical, engineering and industrial areas have been explored by many researchers. However, the use of epoxidized palm oil as resin in composite matrix applications have not been explored and fully realized. Widening the applications of palm oil will give a significant return to the agriculture sector together with the environment. Due to the sustained availability of palm oil in Malaysia, development of new products from palm oil derivatives such as epoxidized palm oil (EPO) has been accorded priority in Malaysia. Consequently, it is beneficial to partly combine the functionalized palm oil to petroleum based thermoset resin to form a new biobased resin.

Unsaturated polyester resin (UPE) is one of the most important thermosetting polymers, which are being used widely in Fibre Reinforced Plastic (FRP) applications. UPE resin are more commonly used than other thermoset resin due to their attractive price per properties ratio (Biron, 2004). In addition, unsaturated polyester resin also possess some good properties such as good mechanical and electrical properties, fairly good heat and creep behaviors, aesthetic, choice of rigidities, resistance to a great number of chemicals, resistance to light, weathering and water in spite of surface deteriorations. It is also easily used in the preparation of composite materials due to the simplicity and flexibility to modify their chemical structure that will allow changes in viscosities and curing time to be used in large variety of applications (Nava and Brooks, 2010) including house-ware, transportation, sports equipment, electrical industries and many more.

This study was focused on developing a new resin by partially blended EPO in UPE as a matrix in kenaf fibre reinforced composites. To improve the loss stiffness of the resin matrix system due to the addition of EPO, MMT nanoclay filler was also added. Kenaf fibre reinforced UPE/EPO/MMT resin was then processed by using resin transfer moulding (RTM).

1.2 Problem Statement

Fibre reinforced unsaturated polyester resin (FRP) is highly preferred in material industries including marine, automotive, sanitary-ware, furniture industries and many more. It was due to its advantages i.e. light in weight, low cost, high strength and elasticity, good thermal and electrical properties, rigid, fairly good heat and creep behaviour and excellent resistance to corrosion. However, the major concern of FRP is its disposal. FRP is very difficult to dispose since it consists of non-biodegradable petroleum based polyester resin and synthetic fibre. Unlike thermoplastic composite, FRP is not considered environmental friendly since it is non-biodegradable, cannot be reused and recycled. The only method to dispose FRP is by cutting it into small fragments and sending to the landfill. This disposal method is considered unsustainable for long run. In order to preserve the environment and to reduce the solid waste volume in landfill, the production of bio-based composite is reinforced.

Bio-based composites have received extra attention in recent years. For example, there are many studies conducted to investigate the use of natural fibres to replace synthetic fibres in polymer composites. It was proven that the natural fibres reinforced unsaturated polyester (UPE) composites enhance better environmental characteristics of the composites (Williams and Wool, 2000). However, the composite does not sufficiently eco-friendly due to the non-biodegradable nature of the synthetic UPE resin matrix (Mohanty *et al.*, 2002a). Thus, the study of polyester based on renewable resource resin to replace synthetic based resin is needed. The synthetic UPE resin was synthesized from chemical reaction of diacid and diols, which are both petroleum based. The depletion of petroleum resources coupled with increasing environmental regulations are acting synergistically to provide the impetus for new materials and products that are compatible with the environment and independent of fossil fuels. However, synthesizing new UPE based resin directly from the vegetable oil has some limitations. This is mainly because the vegetable oil based UPE resin does not show properties of rigidity and performed low mechanical strength which was not suitable for most composite applications especially for

structural applications (Miyagawa *et al.*, 2006a; 2007). Therefore, partially blend vegetable oil with the synthetic UPE resin is required.

Resin transfer moulding (RTM) is one of the common thermoset composite processing method applied in industries. It was due to its advantages i.e. low pressure involves, short production time, perform two sided finishing product, and low processing cost as low skill level operator and less labour service needed. Even though RTM is an advanced processing method, the main concern using RTM is because of the resin flow properties. Poor resin flow properties may affect to the poor fibre wetting which consequently will drop the performance of the resulted composite materials. Thus, attaining a good resin flow with good fibre matrix impregnation was the main focus in RTM processing. RTM mould angle position is one of the factors that has a significant effect on the resin flow properties. However, there are very limited study conducted on the effect of gravitational (RTM mould angle) on the fibre wetting and properties of the resulted composite. In fact, there was no study reported on the effect of mould angle on the natural fibre reinforced modified thermoset/vegetable oil resin.

The production of new composite consists of natural fibre and UPE/vegetable oil resin processed by RTM is a new venture that can be explore. Because of the availability of palm oil in Malaysia, development of new products of eco-friendly UPE resin composites from palm oil derivatives such as EPO has been of particular interest in this project. Thus, the objective of this research is to explore the potential of EPO to be replaced partially in UPE as a matrix in natural fibre reinforced composite, in particular kenaf fibre. In order to improve the stiffness properties of the new resin, MMT nanoclay filler was added. The best formulation of UPE/EPO/MMT blend resin was reinforced with kenaf fibre and the composite prepared using RTM at 0, 30 and 45° mould angle. Following are some of the questions that need to be answered to expand this research area.

- 1) What are the effects of blend ratio of UPE/EPO/MMT resin on thermal characteristic and curing behavior as well as its resistance to moisture absorption?

- 2) What are the effects of blend ratio of UPE/EPO/MMT resin on the mechanical and thermophysical properties of the polymer resin such as tensile, flexural, impact strength, storage modulus and tangent delta?
- 3) What are the dispersion and morphology of EPO and MMT nanoclay inclusion in UPE and the blend of EPO/UPE resin?
- 4) What are the mechanical, thermal and morphological properties of kenaf fibre reinforced UPE/EPO/MMT composite prepared by using RTM process?

It was reported that previously that replacing some of an UPE with vegetable oil has contributed to increase the toughness and altered the thermal properties of the neat UPE resin (Xia and Larock, 2010). However, the increase in toughness seriously lowers the stiffness properties of the new UPE resin. Therefore, the addition of MMT nanoclays was important to improve the stiffness properties of the UPE/vegetable oil resin (Haq et al., 2008, Tan and Chow, 2010). The addition of MMT may also improve the barrier properties between the vegetable oils added and the UPE (Rigoberto Burgueno et al., 2007). The modified UPE/EPO resin reinforced kenaf fibre processed with higher RTM mould angle was provided better fibre wetting and increase the properties of the resulted new composite.

1.3 Objectives of Study

This research aims at developing environmentally friendly composite using UPE/EPO/MMT blend as matrix with the reinforcement of kenaf fibre. The objectives of this study are as follows:

- 1) To investigate the effect of EPO blends on chemical structure and curing behaviour of UPE resin.
- 2) To characterise the effects of EPO content on the mechanical, thermal, thermophysical, morphology and water absorption properties of UPE/EPO resin.

- 3) To characterise the effects of MMT content on the mechanical, thermal, thermophysical, morphology and water absorption properties of UPE/EPO/MMT resin.
- 4) To investigate the effects of different RTM mould angle on the mechanical, thermophysical and morphology properties of kenaf fibre reinforced UPE/EPO/MMT composite.

1.4 Scope of Study

In order to achieve the objectives of the research, the following activities were carried out:

The first part of the study, the modified UPE/EPO resin were prepared with various amounts of EPO (10, 20 and 30 wt %). In this step, the EPO was added into UPE resin and cured in an oven at 100 °C (2 hours) and 160 °C (2 hours) as referred to previous study (Miyagawa *et al.*, 2006a; Miyagawa *et al.*, 2007; Haq *et al.*, 2009a, Haq *et al.*, 2011). The chemical structure of the cured UPE/EPO blend resin was then characterised using Fourier transform infrared (FTIR). In order to understand the curing behaviour of the UPE/EPO blend resin, the uncured UPE/EPO blend resin sample was heated in the differential scanning calorimetry (DSC) and the enthalpy was evaluated. Next, the effect of different EPO content in the UPE/EPO resin on the physical and mechanical properties of the UPE/EPO resin were evaluated by water absorption, tensile, flexural and impact test. The thermal and thermophysical behaviour of the UPE/EPO were also evaluated by using thermogravimetric analysis (TGA) and dynamic mechanical analysis (DMA) test. Lastly, the morphology of the UPE/EPO blend was evaluated using scanning electron microscope (SEM) test.

The second part of the study, MMT filler was added into the UPE/EPO resin system as reinforcement. The UPE/EPO/MMT resin were prepared with various amounts of MMT (1, 1.5 and 2 phr). The physical and mechanical properties of the UPE/EPO/MMT resin were evaluated by water absorption, tensile, flexural and

impact test. The thermal and thermophysical properties of the UPE/EPO/MMT resin were characterised using thermogravimetric analysis (TGA) and dynamic mechanical analysis (DMA) test. The distribution of the MMT nanoclay filler in the system was also being evaluated by using scanning electron microscope (SEM) and transmission electron microscopy (TEM) test. The best UPE/EPO/MMT resin formulations was chosen by selecting the best stiffness-toughness balanced properties of the new fabricated UPE/EPO/MMT resin for further use in the preparation of kenaf fibre reinforcement composite.

The third part of the study, the kenaf fibre reinforced UPE/EPO/MMT composite was prepared by using resin transfer moulding (RTM) processing technique at different mould angle (0° , 30° and 45°). The mechanical properties of the kenaf fibre reinforced UPE/EPO/MMT composite at different RTM mould angles were evaluated by determining tensile, flexural and impact properties. The thermophysical and morphology properties of kenaf fibre reinforced UPE/EPO/MMT composite at different RTM mould angles were also characterised by using dynamic mechanical analysis (DMA) and scanning electron microscope (SEM). Finally, the conclusion has been made on the best RTM mould angle for kenaf fibre reinforced UPE/EPO/MMT composites.

REFERENCE

- Abdullah, A. H., Khalina, A. and Ali, A. (2011). Effect of Fiber Volume Fraction on Unidirectional Kenaf/Epoxy Composites: The Transition Region. *Polymer Plastics Technology and Engineering* 50: 1362-1366.
- Adriana, T., Thiru, A. and Francisco, C. (2013). A Review on The Characteristics Of gomuti Fibre And Its Composites With Thermoset Resins. *Journal Of Reinforced Plastics and Composites*. 32(2): 124-136.
- Ahmad, M., Gharayebi, Y., Salit, M. S., Hussein, M. Z. and Shameli, K. (2011). Comparison of *In Situ* Polymerization and Solution-Dispersion Techniques in the Preparation of Polyimide/Montmorillonite (MMT) Nanocomposites. *International Journal of Polymer Science*. 12: 6040-6050.
- Ahmad, S., Ashraf, S. M., Naqvi, F., Yadav, S. and Hasnat, A. (2003). A polyesteramide from Pongamia glabra oil for biologically safe anticorrosive coating. *Progress in Organic Coatings*. 47(2): 95-102.
- Akil, H. M., Omar, M. F., Mazuki, A. A. M., Safiee, S., Ishak, Z. A. M. and Abu Bakar, A. (2011). Kenaf fiber reinforced composites: A review. *Materials & Design*. 32(8-9): 4107-4121.
- Al-Bahadly, E. A. O. (2013). *The Mechanical Properties of Natural Fiber Composites*. Doctor of Philosophy. Swinburn University of Technology.
- Alavudeen, A., Thiruchitrambalam, M. and Athijayamani, A. (2011). Clutch plate using woven hybrid composite materials. *Materials Research Inovations*. 15(4): 229-234.
- Altuntas, E., Cayl, G., Kusefoglu, S. and Nugay, N. (2008). Renewable Polymeric Nanocomposite Synthesis Using Renewable Functionalized Soybean-Oil-Based Intercalant and Matrix. *Designed Monomers and Polymers*. 11: 371-381.

- Amico, S. and Lekakou, C. (2001). An experiment study of the permeability and capillary pressure in resin-transfer moulding. *Composites Science and Technology*. 61(2001): 1945--1959.
- Annual Report (2013). Kementerian Perusahaan Perladangan dan Komoditi, Lembaga Kenaf Dan Tembakau Negara.
- Anuar, H., Zuraida, A., Kovacs, J. G. and Tabi, T. (2012). Improvement of Mechanical Properties of Injection-Molded Polylactic Acid–Kenaf Fiber Biocomposite. *Journal of Thermoplastic Composite Materials*. 25: 153-164.
- Arsad, A. (2010). *Compatibiliser Effects On Properties of Polyamid-6/Acrylonitrile-Butadiene-Styrene and Polyamide-6/Acrylonitrile-Butadiene-Styrene/Short Glass Fibre Thermoplastic Composites*. Doctor of Philosophy. Universiti Teknologi Malaysia.
- Aziz, S. H., Ansell, M. P., Clarke, S. J. and Panteny, S. R. (2005). Modified polyester resins for natural fibre composites. *Composites Science and Technology*. 65(3–4): 525-535.
- Banno, S., Oshibe, Y. and Nakagawa, Y. (1987). *US4708982 A. Cured unsaturated polyester resin or vinyl ester resin containing flourine-containing groups oriented on its surface. US*
- Basiron, Y. (2005). Palm Oil. In: F. Shahidi. *Bailey's Industrial Oil and Fat Products*. (333-429). John Wiley & Sons, Inc.
- Bavan, S. D. and Kumar, M. G. C. (2013). Maize-Natural Fiber as Reinforcement with Polymers for Structural Applications. In: S. Thomas, M. Sebastian, A. George and Y. Weimin. *Natural Polymers, Biopolymers, Biomaterials, and Their Composites, Blends and IPNs*. United States of America: Apple Academic Press Inc.
- Belgacem, M. N. and Gandini, A. (2008). Materials from Vegetable Oils: Major Sources, Properties and Applications. In: M. N. Belgacem and A. Gandini. *Monomers, Polymers and Composites from Renewable Resources*. (39-66). Amsterdam, Netherlands: Elsevier Ltd.
- Bensadoun, F., Kchit, N., Billotte, C., Bickerton, S., Trochu, F. and Ruiz, E. (2011). A Study of Nanoclay Reinforcement of Biocomposites Made by Liquid Composite Molding. *International Journal of Polymer Science*: 1-10.

- Bharadwaj, R. K., Mehrabi, A. R., Hamilton, C., Trujillo, C., Murga, M., Fan, R., Chavira, A. and Thompson, A. K. (2002). Structure–property relationships in cross-linked polyester–clay nanocomposites. *Polymer*. 43(13): 3699-3705.
- Bickerton, S. and Advani, S. G. (1997). Experimental Investigation and Flow Visualization of the Resin-Transfer Mold-Filling Process in a Non-Planar Geometry. *Composites Science and Technology*. 57(1997): 23-33.
- Bio Tech Mills, I. (2009). Company Overview. Kenaf Plant Characteristic Retrieved 18 Jun 2015, from <http://www.slideshare.net/akimkatsu/biotech-mills-presentation>.
- Biron, M. (2004). Detailed accounts of thermoset resins for moulding and composite matrices. In: *Thermosets and Composites*. New York: Elsevier Ltd.
- Bismarck, A., Mishra, S. and Lampke, T. (2005). Plant Fibers as Reinforcement for Green Composites. In: A. K. Mohanty, M. Misra and L. T. Drzal. *Natural Fibers, Biopolymers, and Biocomposites*. United States: CRC Press.
- Blank, W. J., He, Z. A. and Picci, M. (2001). Catalysis of The Epoxy-Carbonyl Reaction. *International Waterborne, High-Solids and Powder Coatings Symposium*. 21- 23 February. New Orleans, Los Angeles.
- Bordes, P., Pollet, E. and Avérous, L. (2009). Nano-biocomposites: Biodegradable polyester/nanoclay systems. *Progress in Polymer Science*. 34(2): 125-155.
- Bottger, W., Lepelaar, M. and Hensen, L. (2008). From natural fibre reinforced composites to fully bio based composites in RTM technology. 6th N-FibreBased Congress: Naturfaserverstärkte Kunststoffe - within the AVK Tagung/Composites Europe. A. V. Kunststoffe. Frankfurt, Germany, Technische Vereinigung.
- Callaway, J. C. (2004). Hempseed as a nutritional resource: An overview. *Euphytica*. 140(1-2): 65-72.
- Campbell, F. C. (2010). Matrix Resin System. In: *Structural Composite Materials*. (63-99). United States: ASM International.
- Can, E., Küsefoğlu, S. and Wool, R. P. (2002). Rigid thermosetting liquid molding resins from renewable resources. II. Copolymers of soybean oil monoglyceride maleates with neopentyl glycol and bisphenol A maleates. *Journal of Applied Polymer Science*. 83(5): 972-980.

- Caqmpanella, A. and Baltanas, M. A. (2005). Degradation of the oxirane ring of epoxidized vegetable oils in liquid-liquid systems: I Hydrolysis and attack by H₂O₂. *Latin American Applied Research*. 35: 205-210.
- Chandrashekhara, K., Sundararaman, S., Flanigan, V. and Kapila, S. (2005). Affordable composites using renewable materials. *Materials Science and Engineering: A*. 412(1–2): 2-6.
- Charles, L. W. and Venita, K. B. (2002). Plant maturity and kenaf yield components. *Industrial Crops and Products*. 16: 81-88.
- Chawla, K. K. (2005). *Fibrous Material*. Cambridge: Cambridge University Press.
- Chinn, H., Lochner, U. and Ishikawa, Y. (2009). Unsaturated Polyester Resins. CEH Marketing Research Report Menlo Park, California, SRI Consulting. 94025.
- Chua, P. S. (1987). Dynamic mechanical analysis studies of the interphase. *Polymer Composites*. 8(5): 308-313.
- Da Silva Santos, R., de Souza, A. A., De Paoli, M.-A. and de Souza, C. M. L. (2010). Cardanol–formaldehyde thermoset composites reinforced with buriti fibers: Preparation and characterization. *Composites Part A: Applied Science and Manufacturing*. 41(9): 1123-1129.
- Dai, H., Yang, L., Lin, B., Wang, C. and Shi, G. (2009). Synthesis and Characterization of the Different Soy-Based Polyols by Ring Opening of Epoxidized Soybean Oil with Methanol, 1,2-Ethenediol and 1,2-Propanediol. *Journal of the American Oil Chemists' Society*. 86(3): 261-267.
- Dansiri, N., Yanumet, N. and Ellis, J. W. (2002). Resin Transfer Molding of Natural Fiber Reinforced Polybenzoxazine Composites. *Polymer Composites*. 23(3): 352-360.
- De la Caba, K., Guerrero, P., Mondragon, I. and Kenny, J. M. (1998). Comparative study by DSC and FTIR techniques of an unsaturated polyester resin cured at different temperatures. *Polymer International*. 45(4): 333-338.
- Deffense, E. (1985). Fractionation of palm oil. *Journal of the American Oil Chemists' Society*. 62(2): 376-385.
- Deghani, A. (2012). *Mechanical and Thermal Properties of Montmorillonite Filled Date Palm Leaf Fiber Reinforced Recycled Polyethylene Terephthalate Nanocomposites*. Master. Universiti Teknologi Malaysia.

- Deka, H. and Karak, N. (2009). Vegetable Oil-Based Hyperbranched Thermosetting Polyurethane/Clay Nanocomposites. *Nanoscale Research Letter*. 4(7): 758-765.
- Deka, H., Misra, M. and Mohanty, A. (2013). Renewable resource based “all green composites” from kenaf biofiber and poly(furfuryl alcohol) bioresin. *Industrial Crops and Products*. 41: 94-101.
- Dutta, N., Karak, N. and Dolui, S. K. (2004). Synthesis and characterization of polyester resins based on Nahar seed oil. *Progress in Organic Coatings*. 49(2): 146-152.
- Dutta, S. and Karak, N. (2005). Synthesis, characterization of poly(urethane amide) resins from Nahar seed oil for surface coating applications. *Progress in Organic Coatings*. 53(2): 147-152.
- Dweib, M. A., Hu, B., O'Donnell, A., Shenton, H. W. and Wool, R. P. (2004). All natural composite sandwich beams for structural applications. *Composite Structures*. 63(2): 147-157.
- Edeerozey, A. M. M., Akil, H. M., Azhar, A. B. and Ariffin, M. I. Z. (2007). Chemical modification of kenaf fibers. *Materials Letters*. 61(10): 2023-2025.
- Elsaeed, S. M. and Farag, R. K. (2012). Mechanical, thermal and barrier properties of unsaturated polyester Nanocomposite based on et-waste for polymer concrete. *Global Advanced Research Journal of Engineering, Technology and Innovation*. 1(1): 16-24.
- Esfahani, J. M., Sabet, A. R. and Esfandeh, M. (2011). Assessment of nanocomposites based on unsaturated polyester resin/nanoclay under impact loading. *Polymer for Advanced Technologies*. 23(4): 817-824.
- Ferland, P., Guittard, D. and Trochu, F. (1996). Cocurrent Methods for Permeability Measurement in Resin Transfer Molding. *Polymer Composites*. 17(1): 149-158.
- Fink, J. K. (2005). *Reactive Polymers: Fundamentals and Applications: a concise guide to industrial polymers* (1st ed). New York: William Andrew, Inc.
- Frederick, R. P. J. (1997). Simulation of the Injection Process in Resin Transfer Molding. *Polymer Composites*. 18(4): 460-476.

- Fu, S.-Y., Feng, X.-Q., Lauke, B. and Mai, Y.-W. (2008). Effects of particle size, particle/matrix interface adhesion and particle loading on mechanical properties of particulate-polymer composites. *Composite Part B: Engineering*. 39: 933-961.
- Gibbons, W. S., Patel, H. M. and Kusy, R. P. (1997). Effects of plasticizers on the mechanical properties of poly(vinyl chloride) membranes for electrodes and biosensors. *Polymer*. 38(11): 2633-2642.
- Giita Silverajah, V. S., Ibrahim, N. A., Zainuddin, N., Wan Yusuf, W. M. Z. and Abu Hassan, H. (2012a). Mechanical, Thermal and Morphological Properties of Poly(lactic acid)/Epoxidized Palm Olein Blend. *Molecules*. 17(10): 11729-11747.
- Giita Silverajah, V. S., Ibrahim, N. A. I., Wan Yunus, W. M. Z., Abu Hassan, H. and Woei, C. B. (2012b). A Comparative Study on the Mechanical, Thermal and Morphological Characterization of Poly(lactic acid)/Epoxidized Palm Oil Blend. *International Journal of Molecular Sciences*. 13: 5878-5898.
- Giitta Silverajah, V. S., Ibrahim, N. A., Zainuddin, N., Yunus, W. M. Z. W. and Hassan, H. A. (2012). Mechanical, Thermal and Morphological Properties of Poly(lactic acid)/Epoxidized Palm Olein Blend. *Molecules*. 17(10): 11729-11747.
- Gillham, J. K., Benci, J. A. and Noshay, A. (1974). Isothermal transitions of a thermosetting system. *Journal of Polymer Science: Polymer Symposia*. 46(1): 279-289.
- Gonzalez, M. G., Cabanelas, J. C. and Baselga, J. (2012). Application of FTIR on Epoxy Resin - Identification, Monitoring the Curing Process, Phase Separation and Water Uptake. In T. Theophanides. *Infrared Spectroscopy - Materials Science, Engineering and Technology*. (13-25). Shanghai: Intech.
- Gou, J., Zhang, C., Liang, Z., Wang, B. and Simpson, J. (2003). Resin Transfer Molding Process Optimization Using Numerical Simulation and Design of Experiments Approach. *Polymer Composites* 24(1): 1-12.
- Graupner, N., Herrmann, A. S. and Müssig, J. (2009). Natural and man-made cellulose fibre-reinforced poly(lactic acid) (PLA) composites: An overview about mechanical characteristics and application areas. *Composites Part A: Applied Science and Manufacturing*. 40(6-7): 810-821.

- Grimsley, B. W., Hubert, P., Song, X., Cano, R. J., Loos, A. C. and Pipes, R. B. (2001). Flow and Compaction During the Vacuum Assisted Resin Transfer Molding Process. National Aeronautics and Space Administration. United States, Nasa technodoc. 20040086021.
- Gunstone, F. (1993). The study of natural epoxy oils and epoxidized vegetable oils by ^{13}C nuclear magnetic resonance spectroscopy. *Journal of the American Oil Chemists Society*. 70(11): 1139-1144.
- Guo, B., Jia, D. and Cai, C. (2004). Effects of organo-montmorillonite dispersion on thermal stability of epoxy resin nanocomposites. *European Polymer Journal*. 40(2004): 1743-1748.
- Habib, F. and Bajpai, M. (2011). Synthesis and Characterization of Acrylated Epoxidized Soybean Oil For UV Cured Coatings. *Chemistry & Chemical Technology*. 5(3): 317-326.
- Hall, H. L., Bhuta, M. and Zimmerman, J. M. (1998). Kenaf Fiber Reinforced Composite Athletic Wheelchair. *17th Southern Biomedical Engineering Conference*. 6-8 February. Omni San Antonio Hotel, San Antonio, Texas, U.S.A, 5.
- Haq, M., Burgueño, R., Mohanty, A. K. and Misra, M. (2008). Hybrid bio-based composites from blends of unsaturated polyester and soybean oil reinforced with nanoclay and natural fibers. *Composites Science and Technology*. 68(15–16): 3344-3351.
- Haq, M., Burgueño, R., Mohanty, A. K. and Misra, M. (2009a). Bio-based unsaturated polyester/layered silicate nanocomposites: Characterization and thermo-physical properties. *Composites Part A: Applied Science and Manufacturing*. 40(4): 540-547.
- Haq, M., Burgueño, R., Mohanty, A. K. and Misra, M. (2009b). Processing techniques for bio-based unsaturated-polyester/clay nanocomposites: Tensile properties, efficiency, and limits. *Composites Part A: Applied Science and Manufacturing*. 40(4): 394-403.
- Haq, M., Burgueño, R., Mohanty, A. K. and Misra, M. (2011). Bio-based polymer nanocomposites from UPE/EML blends and nanoclay: Development, experimental characterization and limits to synergistic performance. *Composites Part A: Applied Science and Manufacturing*. 42(1): 41-49.

- Hedley, C. W. (1994). *Mold Filling Parameters In Resin Transfer Molding Of Composites*. Master of Science. Montana State University.
- Henz, B. J., Tamma, K. K., Kanapady, R., Ngo, N. D. and Chung, P. W. (2003). Process Modeling of Composites by Resin Transfer Molding: Practical Applications of Sensitivity Analysis for Isothermal Considerations. *International Journal of Numeric Methods for Heat & Fluid Flow*. 13(4): 415-447.
- Higgins, J. S. and Walsh, D. J. (1984). Interactions in polymer blends-relationship between thermodynamic and scattering measurements. *Polymer Engineering & Science*. 24(8): 555-562.
- Hillermeier, R. W. and Seferis, J. C. (2000). Interlayer Toughening of Resin Transfer Molding Composites. *Composites: Part A*. 32: 721-729.
- Ho, C. C. and Chow, M. C. (2000). The effect of the refining process on the interfacial properties of palm oil. *Journal of the American Oil Chemists' Society*. 77(2): 191-199.
- Holbery, J. and Houston, D. (2006). Natural-fiber-reinforced polymer composites in automotive applications. *JOM*. 58(11): 80-86.
- Hong, C. K. and Wool, R. P. (2005). Development of a bio-based composite material from soybean oil and keratin fibers. *Journal of Applied Polymer Science*. 95(6): 1524-1538.
- Huber, T., Graupner, N. and Mussig, J. (2010). Natural Fibre Composite Processing: A Technical Overview. In: J. Mussig. *Industrial Applications of Natural Fibres Structure, Properties and Technical Applications*. United Kingdom: John Wiley & Sons, Ltd.
- Hull, D. and Clyne, T. W. (1996). *An Introduction to Composite Materials*. (2nd ed). Melbourne, Australia: Cambridge University Press.
- Humbert, D. R. (1995). *Modeling of Resin Transfer Molding of Composite Materials with Oriented Unidirectional Plies*. Masters of Science. Montana State University
- Ibrahim, A. N. (2013). *Preparation and Characterization of Palm Fiber Reinforced Poly(e-Caprolactone)/Poly(Lactic Acid) Composites*. Doctor of Philosophy. Universiti Teknologi Malaysia.

- Idris, N., Abdullah, A. and Halim, A. H. (1992). Evaluation of palm oil quality: Correlating sensory with chemical analyses. *Journal of the American Oil Chemists Society*. 69(3): 272-275.
- Inceoglu, A. B. and Yilmazer, U. (2002). Mechanical Properties of Unsaturated Polyester / Montmorillonite Composites. Nanophase and Nanocomposite Materials IV Boston, Massachusetts, Materials Research Society. 703: 387-392.
- Indira, K. N., Parameswaranpillai, J. and Thomas, S. (2013). Mechanical Properties and Failure Topography of Banana Fiber PF Macrocomposites Fabricated by RTM and CM Techniques. *International Scholarly Research Notices* 2013(2013): 8.
- Jawaid, M., Abdul Khalil, H., Abu Bakar, A., Azman Hassan and Dungani, R. (2012). Effect of Jute Fibre Loading On The Mechanical And Thermal Properties Of Palm-Epoxy. *Journal of Composite Materials*. 0(0): 1-9.
- Jawaid, M., Abdul Khalil, H. P. S. and Abu Bakar, A. (2011). Woven hybrid composites: Tensile and flexural properties of oil palm-woven jute fibres based epoxy composites. *Materials Science and Engineering: A*. 528(15): 5190-5195.
- Jēkabsons, N. and Byström, J. (2002). On the effect of stacked fabric layers on the stiffness of a woven composite. *Composites Part B: Engineering*. 33(8): 619-629.
- Jia, Q. M., Zheng, M., Chen, H. X. and Shen, R. J. (2005). Synthesis and characterization of polyurethane/epoxy interpenetrating network nanocomposites with organoclays. *Polymer Bulletin*. 54(1-2): 65-73.
- Jin, U. H. (2007). *Functionalization of Nanoclays Through Exchange Reactions*. Master of Science in Chemical Engineering. New Jersey Institute of Technology.
- Jo, B.-W., Park, S.-K. and Kim, D.-K. (2008). Mechanical properties of nano-MMT reinforced polymer composite and polymer concrete. *Construction and Building Materials*. 22(1): 14-20.
- John, M. J. and Thomas, S. (2008). Biofibres and biocomposites. *Carbohydrate Polymers*. 71(3): 343-364.

- Jr, H. L. O., Bolner, A. S., Fiorio, R., Zattera, A. J. and Amico, S. C. (2010). Mechanical and Dynamic Mechanical Analysis of Hybrid Composites Molded by Resin Transfer Molding. *Journal of Applied Polymer Science*. 118: 887-896.
- Katoch, S. and Kundu, P. P. (2011). Thermal and Mechanical Behavior of Unsaturated Polyester [Derived from Poly(ethylene terephthalate) Waste] and Montmorillonite-Filled Nanocomposites Synthesized by *In Situ* Polymerization. *Journal of Applied Polymer Science*. 122: 2731-2740.
- Katoch, S., Sharma, V. and Kundu, P. P. (2010). Swelling Kinetics of Unsaturated Polyester-layered Silicate Nanocomposite Depending on the Fabrication Method. *diffusion-fundamentals.org*. 13(2010): 1-31.
- Kayode Adekunle, Dan Akesson and Skrifvars, M. (2010). Synthesis of reactive soybean oils for use as a biobased thermoset resins in structural natural fiber composites. *Journal of Applied Polymer Science*. 115(6): 3137-3145.
- Keusch, S. and Haessler, R. (1999). Influence of surface treatment of glass fibers on the dynamic mechanical properties of epoxy resin composites. *Composite Part A: Applied Science and Manufacturing*. 30(8): 997-1002.
- Khalil, H. A., Suraya, N., Atiqah, N., Jawaidd, M. and Hassan, A. (2012). Mechanical and thermal properties of chemical treated kenaf fibres reinforced polyester composites. *Journal of Composite Materials*. 0(0): 1-8.
- Khalil, H. P. S. A., Issam, A. M., Shakri, M. T. A., Suriani, R. and Awang, A. Y. (2007). Conventional agro-composites from chemically modified fibres. *Industrial Crops and Products*. 26: 315-323.
- Khan, A. R. (2011). Kenaf, a fibre for the future: the Harusmas experience. . News, JEC Composites Knowledge & Networking, Harusmas Agro Sdn Bhd. Retrieved 27 February 2013, 2013, from <http://www.jeccomposites.com/content/harusmas-agro-sdn-bhd>.
- Khoo, S. (2010, 29 April). Growing Demand for Kenaf. *The Star*, Retrieved June 15, 2014, from <http://www.thestar.com.my/>.
- Khot, S. N., Lascala, J. J., Can, E., Morye, S. S., Williams, G. I., Palmese, G. R., Kusefoglu, S. H. and Wool, R. P. (2001). Development and application of triglyceride-based polymers and composites. *Journal of Applied Polymer Science*. 82(3): 703-723.

- Kozłowski, R., Władyka-Przybylak, M., Helwig, M. and Kurzydłowski, K. (2004). Composites Based on Lignocellulosic Raw Materials. *Molecular Crystals and Liquid Crystals*. 418(1): 131-151.
- Ku, H., Wang, H., Pattarachaiyakoo, N. and Trada, M. (2011). A review on the tensile properties of natural fiber reinforced polymer composites. *Composites Part B: Engineering*. 42(4): 856-873.
- Kuila, T., Tripathy, T. and Hee Lee, J. (2012). 7 - Polyolefin-based polymer nanocomposites. In: F. Gao. *Advances in Polymer Nanocomposites*. (181-215). Woodhead Publishing.
- Kumari, S., Mishra, A. K., Krishna, A. V. R. and Raju, K. V. S. N. (2007). Organically modified montmorillonite hyperbranched polyurethane-urea hybrid composites. *Progress in Organic Coatings*. 60: 54-62.
- Kurt Demmler, Milan Velic and Zoller, K. (1974). *US Patern No 3,840,617. US: United States Patent and Trademark Office*
- Kushwaha, P. and Kumar, R. (2011). Reinforcing Effect of Nanoclay in Bamboo-Reinforced Thermosetting Resin Composites. *Polymer-Plastics Technology and Engineering*. 50: 127-135.
- La Scala, J. and Wool, R. P. (2005). Property analysis of triglyceride-based thermosets. *Polymer*. 46(1): 61-69.
- Labuschagne, P. W., Moolman, S. and Maity, A. (2012). *Intelligent Nanomaterials*. Canada: John Wiley & Sons, Inc.
- Lai, W. L., Mariatti, M. and Jani S, M. (2008). The Properties of Woven Kenaf and Betel Palm (Areca catechu) Reinforced Unsaturated Polyester Composites. *Polymer-Plastics Technology and Engineering*. 47(12): 1193-1199.
- Lakshmi, M. S., Narmadha, B. and Reddy, B. S. R. (2008). Enhanced thermal stability and structural characteristics of different MMT-Clay/epoxy-nanocomposite materials. *Polymer Degradation and Stability*. 93(1): 201-213.
- LaScala J.J., W. R. P. (2002). Effect of triglyceride structure on epoxidation. . *J Am Oil Chem Soc.* . 79(4): 373-378.
- Laurenzi, S. and Marchetti, M. (2012). Advanced Composite Materials by Resin Transfer Molding for Aerospace Applications. In: N. Hu. *Composites and Their Properties*. United States: InTech.

- Li, F. and Larock, R. C. (2001). New soybean oil-styrene-divinylbenzene thermosetting copolymers. III. Tensile stress-strain behavior. *Journal of Polymer Science Part B: Polymer Physics*. 39(1): 60-77.
- Liu, W., Drzal, L. T., Mohanty, A. K. and Misra, M. (2007a). Influence of processing methods and fiber length on physical properties of kenaf fiber reinforced soy based biocomposites. *Composites Part B: Engineering*. 38(3): 352-359.
- Liu, W., Misra, M., Drzal, L. T. and Mohanty, A. K. (2005a). Influence of processing methods and fiber length on physical properties of kenaf fiber reinforced soy based biocomposites. *20th Technical Conference of the American Society for Composites 2005*. 2111-2121.
- Liu, Z. and Erhan, S. Z. (2008). "Green" composites and nanocomposites from soybean oil. *Materials Science and Engineering: A*. 483-484(0): 708-711.
- Liu, Z., Erhan, S. Z. and Xu, J. (2005b). Preparation, characterization and mechanical properties of epoxidized soybean oil/clay nanocomposites. *Polymer*. 46(23): 10119-10127.
- Liu, Z. S., Erhan, S. Z. and Calvert, P. D. (2007b). Solid freeform fabrication of epoxidized soybean oil/epoxy composite with bis or polyalkyleneamine curing agents. *Composites Part A: Applied Science and Manufacturing*. 38(1): 87-93.
- Lu, J., Hong, C. K. and Wool, R. P. (2004). Bio-based nanocomposites from functionalized plant oils and layered silicate. *Journal of Polymer Science Part B: Polymer Physics*. 42(8): 1441-1450.
- Lu, J., Khot, S. and Wool, R. P. (2005). New sheet molding compound resins from soybean oil. I. Synthesis and characterization. *Polymer*. 46(1): 71-80.
- Lu, J. and Wool, R. P. (2008). Additive toughening effects on new bio-based thermosetting resins from plant oils. *Composites Science and Technology*. 68(3-4): 1025-1033.
- Ma, J., Xu, J., Ren, J.-H., Yu, Z.-Z. and Mai, Y.-W. (2003). A new approach to polymer/montmorillonite nanocomposites. *Polymer*. 44(16): 4619-4624.
- Mahapatra, S. S. and Karak, N. (2004). Synthesis and characterization of polyesteramide resins from Nahar seed oil for surface coating applications. *Progress in Organic Coatings*. 51(2): 103-108.

- Manfredi, L. B., Santis, H. D. and Vazquez, A. (2008). Influence of the addition of montmorillonite to the matrix of unidirectional glass fibre/epoxy composites on their mechanical and water absorption properties. *Composite Part A*. 39: 1726-1731.
- Manoharan, S., Suresha, B., Ramadoss, G. and Bharath, B. (2014). Effect of Short Fiber Reinforcement on Mechanical Properties of Hybrid Phenolic Composites. *Journal of Materials*. 2014: 1-9.
- Manthey, N. W. (2013). *Development of Hemp Oil Based Bioresins for Biocomposites*. Doctor of Philosophy. University of Southern Queensland.
- Markus Henne, Paolo Ermanni, Myl ene Del eglise and Krawczak, P. (2004). Heat transfer of fibre beds in resin transfer moulding: an experimental approach. *Composites Science and Technology*. 64: 1191–1202.
- Mazuki, A. A. M., Akil, H. M., Safiee, S., Ishak, Z. A. M. and Bakar, A. A. (2011). Degradation of dynamic mechanical properties of pultruded kenaf fiber reinforced composites after immersion in various solutions. *Composites Part B: Engineering*. 42(1): 71-76.
- Mazumdar, S. (2001). *Composites Manufacturing: Materials, Product, and Processing Engineering*. United States of America: CRC Press
- McAlpine, M. and Bennett, C. (2010). *EP2250030A1*. Improvements in thermal transfer printing.
- McAlpine, M. and Bennett, C. (2011). *US 20110000028 A1*. Thermal transfer printing.
- Mehdi Poorabdollah, Mohammad Hosain Beheshty and Vafayan, M. (2011). The effect of nanoclay on curing unsaturated polyester resin. *Society of Plastics Engineers (SPE)*. Spepro.003854: 1-2.
- Mehta, G., Mohanty, A. K., Misra, M. and Drzal, L. T. (2004). Biobased resin as a toughening agent for biocomposites. *Green Chemistry*. 6(5): 254-258.
- Michael, A. R. M., Jurgens, O. M. and Ulrich, S. S. (2007). Plant oil renewable resources as green alternatives in polymer science. *The Royal Society of Chemistry*. 36: 1788-1802.
- Mittal, A., Katahira, R., Himmel, M. E. and Johnson, D. K. (2011). Effect of alkaline or liquid ammonia treatment on crystalline cellulose in crystalline structure and effects on enzymatic digestibility. *Biotechnol Biofuels*. 4(41).

- Miyagawa, H., Misra, M., Drzal, L. T. and Mohanty, A. K. (2005). Fracture toughness and impact strength of anhydride-cured biobased epoxy. *Polymer Engineering & Science*. 45(4): 487-495.
- Miyagawa, H., Mohanty, A. K., Burgueno, R., Drzal, L. T. and Misra, M. (2006a). Development of Biobased Unsaturated Polyester Containing Functionalized Linseed Oil. *Industrial & Engineering Chemistry Research*. 45: 1014-1018.
- Miyagawa, H., Mohanty, A. K., Burgueño, R., Drzal, L. T. and Misra, M. (2006b). Characterization and Thermophysical Properties of Unsaturated Polyester-Layered Silicate Nanocomposites. *Journal of Nanoscience and Nanotechnology*. 6(2): 464-471.
- Miyagawa, H., Mohanty, A. K., Burgueño, R., Drzal, L. T. and Misra, M. (2007). Novel biobased resins from blends of functionalized soybean oil and unsaturated polyester resin. *Journal of Polymer Science Part B: Polymer Physics*. 45(6): 698-704.
- Mohamed Yusoff, M. Z. (2009). *Mechanical Properties of Oil Palm Fibre-Thermoset Composites*. Master. Universiti Putra Malaysia.
- Mohanty, A. K., Misra, M. and Drzal, L. T. (2002a). Sustainable Bio-Composites from Renewable Resources: Opportunities and Challenges in the Green Materials World. *Journal of Polymers and the Environment*. 10(1): 19-26.
- Mohanty, A. K., Misra, M. and Drzal, L. T. (2002b). Sustainable Bio-Composites from Renewable Resources: Opportunities and Challenges in the Green Materials World. *Journal of Polymers and the Environment*. 10(1-2): 19-26.
- Mohanty, A. K., Misra, M. and Hinrichsen, G. (2000). Biofibres, biodegradable polymers and biocomposites: An overview. *Macromolecular Materials and Engineering*. 276-277(1): 1-24.
- Molajavadi, V. and Garmabi, H. (2011). Predicting the Young's modulus of intercalated and exfoliated polymer/clay nanocomposites. *e-Polymers*. 20: 1-12.
- Mosiewicki, M. A. and Aranguren, M. I. (2013). A short review on novel biocomposites based on plant oil precursors. *European Polymer Journal*. 49: 1243-1256.
- Mukherjee, T. and Kao, N. (2011). PLA Based Biopolymer Reinforced with Natural Fibre: A Review. *Journal Polymer Environment*. 19: 714-725.

- Nam, S. and Netravali, A. (2006). Green composites. II. Environment-friendly, biodegradable composites using ramie fibers and soy protein concentrate (SPC) resin. *Fibers and Polymers*. 7(4): 380-388.
- Narteh, A. T., Hosur, M. V., Triggs, E. and Jelaani, S. (2013). Effects of Surface Treatments of Montmorillonite Nanoclay on Cure Behavior of Diglycidyl Ether of Bisphenol A Epoxy Resin. *Journal of Nanoscience* 2013: 1-12.
- Nava, H. and Brooks, S. (2010). *Soybean Based Hybrid Unsaturated Polyester Resin System*. Technical Paper at Composites 2010 exhibition: Reichhold.
- Ngo, N. D., Mohan, R. V., Chung, P. W. and Tamma, K. K. (1998). Recent Developments Encompassing Non-Isothermal Liquid Composite Molding Process Modeling/Analysis: Physically Accurate, Computationally Effective, and Affordable Simulations and Validations. *Journal of Thermoplastic Composite Materials*. 11: 493-532.
- Nishino, T., Hirao, K., Kotera, M., Nakamae, K. and Inagaki, H. (2003). Kenaf reinforced biodegradable composite. *Composites Science and Technology*. 63(9): 1281-1286.
- Noh, M. W. and Lee, D. C. (1999). Synthesis and characterization of PS-clay nanocomposite by emulsion polymerization. *Polymer Bulletin*. 42: 619-626.
- Nuhiji, B., Attard, D., Thorogood, G., Hanley, T., Magniez, K., Bungur, J. and Fox, B. (2013). The Effect of a Rapid Heating Rate, Mechanical Vibration and Surfactant Chemistry on the Structure-Property Relationships of Epoxy/Clay Nanocomposites. *Materials* 6: 3624-3640.
- O'Dell, J. L. (1997). Natural Fibers in Resin Transfer Molded Composites. *The Fourth International Conference on Woodfiber-Plastic Composites*. Madison, USA, 280-285.
- O'Donnell, A., Dweib, M. A. and Wool, R. P. (2004). Natural fiber composites with plant oil-based resin. *Composites Science and Technology*. 64(9): 1135-1145.
- Oksman, K. (2001). High Quality Flax Fibre Composites Manufactured by the Resin Transfer Moulding Process. *Journal of Reinforced Plastics and Composites*. 20(7): 621-627.
- Olad, A. (2011). Polymer/Clay Nanocomposite. In B. Reddy. *Diverse Industrial Applications of Nanocomposites*. Croatia: InTech.

- Padmanabhan, S. K. and Pitchumani, R. (1999). Stochastic modeling of nonisothermal flow during resin transfer molding. *International Journal of Heat and Mass Transfer*. 42: 3057-3070.
- Padmasiri, K. G., Micheal, O. B. and Karunanayake, L. (2009). Epoxidation of some vegetable oils and their hydrolysed products with peroxyformic acid - optimised to industrial scale. *J.Natn.Sci.Foundation Sri Lanka*. 37(4): 229-240.
- Paiva, L. B., Morales, A. R., Branciforti, M. C. and Bretas, R. E. S. (2012). Organophilic bentonites based on Argentinean and Brazilian bentonites. Part 2: potential evaluation to obtain nanocomposites. *Brazilian Journal of Chemical Engineering*. 29(4): 751-762.
- Pan, P., Zhu, B., Dong, T., Serizawa, S., Iji, M. and Inoue, Y. (2008). Kenaf fiber/poly(ϵ -caprolactone) biocomposite with enhanced crystallization rate and mechanical properties. *Journal of Applied Polymer Science*. 107(6): 3512-3519.
- Park, J., Ye, Q., Topp, E., Lee, C., Kostoryz, E., Misra, A. and Spencer, P. (2009). Dynamic mechanical analysis and esterase degradation of dentin adhesives containing a branched methacrylate. *Journal of Biomedical Materials Research Part B*. 1: 61-70.
- Park, S.-J., Jin, F.-L. and Lee, J.-R. (2004). Thermal and mechanical properties of tetrafunctional epoxy resin toughened with epoxidized soybean oil. *Materials Science and Engineering: A*. 374(1-2): 109-114.
- Patel, H. S. and Naji, A. M. (2011). Studies on [(tetrahydrophthalated cyclohexanone-formaldehyde resin)-(epoxy resin)] condensates. *Pelagia Research Library*. 2(2): 98-117.
- Paul, D. M. and Smith, C. A. (2002). Kenaf seed storage duration on germination, emergence, and yield. *Industrial Crops and Products*. 17: 9-14.
- Paul, S. A., Joseph, K., Mathew, G. D. G., Pothen, L. A. and Thomas, S. (2010). Influence of polarity parameters on the mechanical properties of composites from polypropylene fiber and short banana fiber. *Composites Part A: Applied Science and Manufacturing*. 41(10): 1380-1387.
- Pfister, D. P. and Larock, R. C. (2010). Green composites from a conjugated linseed oil-based resin and wheat straw. *Composites Part A: Applied Science and Manufacturing*. 41(9): 1279-1288.

- Pfister, D. P., Xia, Y. and Larock, R. C. (2011). Recent Advances in Vegetable Oil-Based Polyurethanes. *ChemSusChem*. 4(6): 703-717.
- Pickering, S. J. (2005). Recycling technologies for thermoset composite materials—current status. *Composites: Part A*. 37: 1206-1215.
- Pothan, L. A., Oommen, Z. and Thomas, S. (2003). Dynamic mechanical analysis of banana fiber reinforced polyester composites. *Composites Science and Technology*. 63(2): 283-293.
- Preghenella, M., Pegoretti, A. and Migliaresi, C. (2005). Thermo-mechanical characterization of fumed silica-epoxy nanocomposites. *Polymer*. 46: 12065-12072.
- Pua, F.-L., Sapuan, S. M., Zainudin, E. S. and Adib, M. Z. (2013). Effect of Fibre Surface Modification on Properties of Kenaf/Poly(vinyl alcohol) Composite Film. *Journal of Biobased Materials and Bioenergy*. 7: 95-101.
- Puing, G. L. I. (2006). *Biobased Thermosets fom Vegetable Oils. Synthesis, Characterization, and Properties*. Doctor of Philosophy. University Rovira I Virgili.
- Rahmat, A. R. (2002). *Microwave Assisted Resin Transfer Moulding*. Doctor of Phylosophy. University of Manchester Institute of Science and Technology (UMIST).
- Ramarad, S. (2008). *Preparation And Properties Of Kenaf Bast Fiber Filled (Plasticized) Poly(Lactic Acid) Composites*. Master. Universiti Sains Malaysia.
- Rashdi, A. A. A., Salit, M. S., Abdan, K. and Megat, M. M. H. (2010). Water Absorption Behaviour of Kenaf Reinforced Unsaturated Polyester Composites and Its Influence on Their Mechanical Properties. *Pertanika Journal Science & Technology*. 18(2): 433-440.
- Rashdi, A. A. A., Sapuan, S. M., Ahmad, M. M. H. and Abdan, K. (2009). Review of kenaf fibre reinforced polymer composite. *Polymer*. 54(777-780).
- Razak, M. Z. A., Arsad, A., Rahmat, A. R. and Hassan, A. (2012). Influence of MMT as reinforcement on rheological behaviour, mechanical and morphological properties of recycled PET/ABS thermoplastic nanocomposites. *Journal of Polymer Engineering*. 32: 177-183.
- Reinchold, I. (2009) *An Engineer's Guide to FRP Technology*. FRP Material Selection Guide.

- Rejab, M. R. M., Theng, C. W., Rahman, M. M., Noor, M. M. and Rose, A. N. M. (2008). An Investigation into the Effects of Fibre Volume Fraction on GFRP Plate. *Malaysian Technical Universitites Conference on Engineering and Technoogy*. March, 8-10. Putra Palace, Perlis, Malaysia.
- Ren, X., Qiu, R., Fifield, L. S., Simmons, K. L. and Li, K. (2012). Effects of Surface Treatments on Mechanical Properties and Water Resistance of Kenaf Fiber-Reinforced Unsaturated Polyester Composites. *Journal of Adhesion Science and Technology* 26(2012): 2277-2289.
- Richard, P. W. (2005). Polymers and Composite Resins from Plant Oil. In Richard P. Wool and X. S. Sun. *Bio-Based Polymers and Composites*. (6-113). USA: Elsevier Academic Press.
- Richard Wool, S. K., Giuseppe Palmese, Shrikant Khot, Ralph Zhao (2000). *High modulus polymers and composites from plant oil* (C09F 100; C08F12210; C08F22210; A61F 200). US
- Richardson, M. O. W. and Zhang, Z. Y. (2000). Experimental investigation and flow visualisation of the resin transfer mould filling process for non-woven hemp reinforced phenolic composites. *Composites Part A: Applied Science and Manufacturing*. 31(12): 1303-1310.
- Rigas, E. J., Mulkern, T. J., Walsh, S. M. and Nguyen, S. P. (2001). Effects of Processing Conditions on Vacuum Assisted Resin Transfer Molding Process (VARTM). Army Research Laboratory. C. Klug, E. Fine and M. Poot. US, Weapons and Materials Research Directorate, ARL. ARL-TR-2480.
- Rigoberto Burgueno, Mahmoodul Haq, Amar K. Mohanty and Misra, M. (2007). Hybrid Bio-Based Composites From Nano-Reinforced Bio-Petro Polymer Blends And Natural Fibers. SPE ACCE Conference-SPE Automotive Division, 53-64.
- Robinson, F. E. (1998). Kenaf: a new fiber crop for paper production. *California Agriculture*. September-October: 31-32.
- Roopesh, M., Bruce, K. F. and Suresh, G. A. (1999). Use of Genetic Algorithms to Optimize Gate and Vent Locations for the Resin Transfer Molding Process. *Polymer Composites*. 20(2): 167-178.
- Rouison, D., Sain, M. and Couturier, M. (2004). Resin transfer molding of natural fiber reinforced composites: cure simulation. *Composites Science and Technology*. 64(5): 629-644.

- Rowell, R. M. (1998). The State Of Art And Future Development Of Bio-based Composite Science And Technology Towards The 21st Century. *The fourth Pacific Rim bio-based composites symposium*. November 2-5. Indonesia, 1-18.
- Rupilius, W. and Ahmad, S. (2005). The Changing World of Oleochemicals. *Palm Oil Developments*. 44: 15-28.
- Saba, N., Paridah, M. T. and Jawaidd, M. (2015). Mechanical properties of kenaf fibre reinforced polymer composite: A review. *Construction and Building Materials*. 76(2015): 87-96.
- Sacristan, M., ROna, J. C., Galia, M. and Cadiz, V. (2010). Synthesis and properties of boron-containing soybean oil based thermosetting copolymers. *Polymer*. 51: 6099-6106.
- Saijun, D., Nakason, C., Kaesaman, A. and Klinpituksa, P. (2009). Water absorption and mechanical properties of water-swellaable natural rubber. *Songklanakarin Journal of Science and Tehnology*. 31: 561-565.
- Sakarya, M. and Deniz, S. (2014). Polyurethane Networks From Different Soy-Based Polyols by The Ring Opening of Epoxidized Soybean Oil With Poly(ethylene glycol)s. *2nd International Symposium On Innovative Technologies In Engineering And Science*. Karabuk University, Turkey, 1394-1402.
- Samsudin, S. A. (2010). *The Thermal Behaviour And Isothermal Crystallisation Of Cyclic Poly (Butylene Terephthalate) And Its Blends*. Doctor of Philosophy. University of Birmingham.
- Sanchez, L., Garcia, D., Balart, R. and Parres, F. (2005). Aging of Polyester Matrix In Saline Water. In G. E. Zaiov and A. Jimenez. *New Developments in Polymer Analysis, Stabilization and Degradation*. (101-114). New York: Nova Science, Inc.
- Scrimgeour, C. (2005). Chemistry of Fatty Acids. In F. Shahidi. *Bailey's Industrial Oil and Fat Products* Scotland: John Wiley & Sons, Inc.
- Sèbe, G., Cetin, N., Hill, C. S. and Hughes, M. (2000). RTM Hemp Fibre-Reinforced Polyester Composites. *Applied Composite Materials*. 7(5-6): 341-349.
- Selvakumar, V., Palanikumar, K. and Palanivelu, K. (2010a). Studies on Mechanical Characterization of Polypropylene/Na⁺-MMT Nanocomposites. *Journal of Minerals & Materials Characterization & Engineering*. 9(8): 671-681.

- Selvakumar, V., Palanikumar, K. and Palanivelu, K. (2010b). Studies on Mechanical Characterization of Polypropylene/Na⁺-MMT Nanocomposites. *Journal of Minerals & Materials Characterization & Engineering*. 9(8): 671-681.
- Sen, S., Gundem, H. B. and Ortac, B. (2013). Property Enhancement in Unsaturated Polyester Nanocomposites by Using a Reactive Intercalant for Clay Modification. *Journal of Applied Polymer Science*: 3247-3254.
- Shaharuddin, S. I. S., Salit, M. S. and Zainudin, E. S. (2006). A Review of the Effect of Moulding Parameters on the Performance of Polymeric Composite Injection Moulding. *Turkish J. Eng. Env. Sci.* 30(2006): 23-34.
- Sharma, V. and Kundu, P. P. (2006). Addition polymers from natural oils—A review. *Progress in Polymer Science*. 31(11): 983-1008.
- Sharma, V. and Kundu, P. P. (2008). Condensation polymers from natural oils. *Progress in Polymer Science*. 33(12): 1199-1215.
- Shen, C.-H. and Springer, G. S. (1976). Moisture Absorption and Desorption of Composite Materials. *Journal of Composite Materials*. 10: 2-20.
- Shia, D., Hui, C. Y., Burnside, S. D. and Giannelis, E. P. (1998). An interface model for the prediction of Young's modulus of layered silicate-elastomer nanocomposites. *Polymer Composites*. 19(5): 608-617.
- Sichina, W. J. (2000). Characterization of Epoxy Resins Using DSC. Thermal Analysis. Norwalk, U.S.A, Perkin Elmer Instruments: 1-4.
- Sigh, R., Erickson, B. and Winters, P. (2009). Bio-Based Strategy: Food and Non-Food Markets. In W. Smitthipong, R. Chollakup and M. Nardin. *Bio-Based Composites For High-Performance Materials From Strategy to Industrial Application*. United States: Taylor & Francis Group.
- Singla, P., Mehta, R. and Upadhyay, S. N. (2012). Clay Modification by the Use of Organic Cations. *Green and Sustainable Chemistry*. 2: 21-25.
- Sinha Ray, S. and Okamoto, M. (2003). Polymer/layered silicate nanocomposites: a review from preparation to processing. *Progress in Polymer Science*. 28(11): 1539-1641.
- Sirapanichart, S., Monvisade, P., Siriphannon, P. and Nukeaw, J. (2011). Poly(methyl methacrylate-co-butyl acrylate)/ Organophosphate-modified Montmorillonite Composites. *Iranian Polymer Journal*. 20(10): 803-811.

- Sithique, M. A. and Alagar, M. (2010). Preparation And Properties Of Bio-Based Nanocomposites From Epoxidized Soy Bean Oil And Layered Silicate. *Malaysian Polymer Journal*. 5(2): 151-161.
- Skrifvars, M. (2000). *Synthetic Modification And Characterisation Of Unsaturated Polyesters*. Academic Dissertation. Laboratory of Polymer Chemistry, Faculty of Science, University of Helsinki.
- Solomons, T. W. G. and Fryhle, C. B. (2008). *Organic Chemistry*. Hoboken: John Wiley & Sons, Inc.
- Sreekumar, P. A., Joseph, K., Unnikrishnan, G. and Thomas, S. (2007). A comparative study on mechanical properties of sisal-leaf fibre-reinforced polyester composites prepared by resin transfer and compression moulding techniques. *Composites Science and Technology*. 67(3–4): 453-461.
- Sreekumar, P. A., Thomas, S. P., Saiter, J. m., Joseph, K., Unnikrishnan, G. and Thomas, S. (2009). Effect of fiber surface modification on the mechanical and water absorption characteristics of sisal/polyester composites fabricated by resin transfer molding. *Composite: Part A*. 40(2009): 1777-1784.
- Sridhar, R. (2013). *Development and Characterization of Nanoclay Dispersed Polymer Composites for Naval Applications*. Doctor of Philosophy. Kuvempu University.
- Srivastava, A. and Prasad, R. (1999). Triglycerides-based diesel fuels. *Renewable and Sustainable Energy Reviews*. 4: 111-133.
- Suh, D. J., Lim, Y. T. and Park, O. O. (2000). The Property and Formation Mechanism of Unsaturated Polyester-Layered Silicate Nanocomposite Depending on the Fabrication Method. *Polymer*. 41: 8557-8563.
- Suresh, S. N. and Kong, X. (2005). Vegetable oils in Production of Polymers and Plastics. In: F. Shahidi. *Bailey's Industrial Oil and Fat Products*. (279-306). Canada: John Wiley & Sons, Inc.
- Sybil, P. P. (1992). McGraw-Hill encyclopedia of science & technology, McGraw-Hill, Inc.
- Tajvidi, M., Najafi, S. K. and Moteei, N. (2006). Long-term water uptake behavior of natural fiber/polypropylene composites. *Journal of Applied Polymer Science*. 99(5): 2199-2203.

- Takashi Nishino^a, Koichi Hirao^a, Masaru Kotera^a, Katsuhiko Nakamae^a and Inagakib., H. (2003). Kenaf reinforced biodegradable composite. *Composites Science and Technology*. 63: 1281–1286.
- Tan, S. G. and Chow, W. S. (2010). Thermal Properties, Fracture Toughness and Water Absorption of Epoxy-Palm Oil Blends. *Polymer-Plastics Technology and Engineering*. 49(9): 900-907.
- Tan, S. G. and Chow, W. S. (2011a). Curing Characteristics and Thermal Properties of Epoxidized Soybean Oil Based Thermosetting Resin. *Journal of the American Oil Chemists' Society*. 88(7): 915-923.
- Tan, S. G. and Chow, W. S. (2011b). Thermal Properties, curing characteristics and water absorption of soybean oil-based thermoset. *Express Polymer Letter*. 5(6): 480-492.
- Tantatherdtam, R., Chollakup, R. and Smitthipong, W. (2015). Mechanical Properties of Natural Fiber-Reinforced Composites. In W. Smitthipong, R. Chollakup and M. Nardin. *Bio-Based Composites for High-Performance Materials From Strategy to Industrial Application*. US: Taylor & Francis Group.
- Tarte, N. H., Cui, L. and Woo, S. (2013). Polyolefin/Layered Silicate Nanocomposites Prepare by In Situ Polymerization. *Advance Polymer Science*. 258(2013): 311-340.
- Thielemans, W., McAninch, I. M., Barron, V., Blau, W. J. and Wool, R. P. (2005). Impure Carbon Nanotubes as Reinforcements for Acrylated Epoxidized Soy Oil Composites. *Journal of Applied Polymer Science*. 98: 1325-1338.
- Thiruchitrambalam, M., Alavudeen, A. and Venkateshwaran, N. (2012). Review on Kenaf Fiber Composites. *Review Material Science*. 32(2012): 106-112.
- Trochu, F., Gauvin, R. and Gao, D. M. (1993). Numerical Analysis of the Resin Transfer Molding Process by the Finite Element Method. *Advances in Polymer Technology*. 12(4): 329-342.
- Trujillo, E., Osorio, L., Van Vuure, A. W., Ivens, J. and Verpoest, I. (2010). Characterization Of Polymer Composite Materials Based On Bamboo Fibres. *14th European Conference On Composite Materials*. 7-10 June 2010. Budapest, Hungary.
- Uddin, F. (2008). Clays, Nanoclays, and Montmorillonite Minerals. *Metallurgical and Materials Transactions A*. 39(12): 2804-2814.

- Udoeyo, F. F. and Adetifa, A. (2012). Characteristics of Kenaf Fiber-Reinforced Mortar Composites. *IJRRAS*. 1121(1): 18-26.
- United States Department of Agriculture (USDA) (2015). Oilseeds: World Markets and Trade. W. A. O. Board. United States, Department of Agriculture, Foreign Agricultural Service.
- Uyama, H., Kuwabara, M., Tsujimoto, T., Nakano, M., Ususki, A. and Kobayashi, S. (2003). Green Nanocomposites from Renewable Resources: Plant Oil-Clay Hybrid Materials. *Chemistry of Materials*. 15: 2492-2494.
- Vargiu, S. (1975). *US Patern No 3,917,522. United States: United States Patent and Trademark Office.*
- Vilay, V., Mariatti, M., MatTaib, R. and Todo, M. (2008). Effect of fiber surface treatment and fiber loading on the properties of bagasse fiber-reinforced unsaturated polyester composites. *Composite Science Technology*. 68: 631-638.
- Wan Rosli, W. D., Kumar, R. N., Mek Zah, S. and Hilmi, M. M. (2003). UV radiation curing of epoxidized palm oil–cycloaliphatic diepoxide system induced by cationic photoinitiators for surface coatings. *European Polymer Journal*. 39(3): 593-600.
- Weisstein, E. W. (2014). Gaussian Function. Mathworld, 2014, from <http://mathworld.wolfram.com/GaussianFunction.html>.
- Williams, G. I. and Wool, R. P. (2000). Composites from Natural Fibers and Soy Oil Resins. *Applied Composite Materials*. 7(5): 421-432.
- Wypych, G. (2004). Effect of Plasticizer On Properties Plasticized Materials. In: W. George. *Handbook of Plasticizer*. Toronto, Canada: ChemTec Publishing.
- Xia, Y. and Larock, R. C. (2010). Critical review: Vegetable oil-based polymeric materials: synthesis, properties, and applications. *Green Chemistry*. 12: 1893-1909.
- Xidas, P. I. and Triantafyllidis, K. S. (2010). Effect of the type of alkylammonium ion clay modifier on the structure and thermal/mechanical properties of glassy and rubbery epoxy–clay nanocomposites. *European Polymer Journal*. 46(3): 404-417.
- Yang, Y. S. and Lee, L. J. (1988). Microstructure formation in the cure of unsaturated polyester resins. *Polymer*. 29(10): 1793-1800.

- Yoon, M.-K., Baidoo, J., Gillespie, J. W. and Heider, D. (2005). Vacuum Assisted Resin Transfer Molding (VARTM) Process Incorporating Gravitational Effects: A Closed-form Solution. *Journal of Composite Materials*. 39(24): 2227-2242.
- Yu, Z., Yin, J., Yan, S., Xie, Y., Ma, J. and Chen, X. (2007). Biodegradable poly(l-lactide)/poly(ϵ -caprolactone)-modified montmorillonite nanocomposites: Preparation and characterization. *Polymer*. 48(21): 6439-6447.
- Zampaloni, M., Pourboghra, F., Yankovich, S. A., Rodgers, B. N., Moore, J., Drzal, L. T., Mohanty, A. K. and Misra, M. (2007). Kenaf natural fiber reinforced polypropylene composites: A discussion on manufacturing problems and solutions. *Composites Part A: Applied Science and Manufacturing*. 38: 1569–1580.
- Zhu, J., Chandrashekhara, K., Flanigan, V. and Kapila, S. (2004). Manufacturing and mechanical properties of soy-based composites using pultrusion. *Composites Part A: Applied Science and Manufacturing*. 35(1): 95-101.
- Zlatanić, A., Lava, C., Zhang, W. and Petrović, Z. S. (2004). Effect of structure on properties of polyols and polyurethanes based on different vegetable oils. *Journal of Polymer Science Part B: Polymer Physics*. 42(5): 809-819.